



Europäisches Patentamt
European Patent Office
Office européen des brevets



Publication number:

0 577 189 A2

12

EUROPEAN PATENT APPLICATION

21 Application number: 93201807.0

51 Int. Cl.⁵: G03C 1/83, G03C 5/16,
G03C 1/26

72 Date of filing: 23.06.93

30 Priority: 30.06.92 US 906621

43 Date of publication of application:
05.01.94 Bulletin 94/01

24 Designated Contracting States:
BE CH DE FR GB IT LI NL

71 Applicant: EASTMAN KODAK COMPANY
343 State Street
Rochester, New York 14650-2201(US)

72 Inventor: Adin, Anthony
Eastman Kodak Company,
343 State Street
Rochester, New York 14650-2201(US)
Inventor: Parton, Richard Lee
Eastman Kodak Company,
343 State Street
Rochester, New York 14650-2201(US)

74 Representative: Nunney, Ronald Frederick
Adolphe et al
Kodak Limited
Patent Department
Headstone Drive
Harrow Middlesex HA1 4TY (GB)

50 Radiation sensitive element with absorber dye to enhance spectral sensitivity range.

57 A radiation detecting element, particularly a photographic element having a radiation detecting composition, in particular a silver halide emulsion. The composition provides the element with a wavelength of peak sensitivity, $\lambda_{peakens}$, and a decreasing sensitivity around $\lambda_{peakens}$. An absorber dye of defined characteristics is chosen, which has the effect of decreasing the change in sensitivity which the element otherwise has without the absorber dye (that is, the absorber dye increases the wavelength range over which the sensitivity is relatively constant). The element is preferably sensitive to infra-red.

EP 0 577 189 A2

EP 0 577 189 A2

Field of the Invention

This invention relates to a radiation sensitive element, particularly a photographic element, which uses an absorber dye to attain a sensitivity of the element which is less sensitive to wavelength changes of incident radiation.

Background of the Invention

A favoured technique for detecting radiation is through the use of a photographic element containing a silver halide emulsion. Such an element is usually exposed with light (which includes infra-red and ultraviolet as well as visible light) in order to form a latent image that is developed during photographic processing to form a visible image. Silver halide is intrinsically sensitive only to light in the blue region of the spectrum.

It is well known to use sensitizing dyes to sensitize the silver halide to other than the blue region (for example, to other areas of the visible spectrum or to infrared light). Sensitizing dyes are chromophoric compounds (usually cyanine dye compounds). Their usual function is to adsorb to the silver halide and to absorb light (usually other than blue light) and transfer that energy via an electron to the silver halide grain thus, rendering the silver halide sensitive to radiation of a wavelength other than the blue intrinsic sensitivity. However, sensitizing dyes can also be used to augment the sensitivity of silver halide in the blue region of the spectrum. The resulting sensitized emulsion will generally have a sensitivity versus wavelength curve with a peak sensitivity the same as, or close to, the wavelength of peak absorption of the sensitizing dye used. The sensitivity curve will then fall off fairly rapidly on either side of the peak sensitivity wavelength.

One particular application of photographic elements in the form of paper or film, is for recording the output from devices such as laser printers which are designed to reproduce black and white or color digitized photographic images. Those printers operate by scanning a photographic element with a controlled laser beam modulated in accordance with the digital image. Following exposure, the photographic element is developed in the same manner as other photographic materials. Typically, the laser beam is in the infrared region, for example 780nm, and is generated by laser diodes. Any color couplers incorporated in such a silver halide emulsion therefore produce a falsecolor image.

A difficulty with printers of the foregoing type is that the laser diodes vary in their output wavelength from diode to diode. For example, manufacturers may specify the wavelength of a monochrome printer being 780nm \pm 20nm. Thus, there may be variation in wavelengths within a given printer using multiple diodes, as well as between printers. Since the sensitized emulsion has a wavelength dependent sensitivity curve as described above, the undesirable result is that the intensity of a given point to be recorded on the photographic element may vary from diode to diode and printer to printer. In view of this situation, IR sensitive films and papers used in such printers desirably have a constant photographic response over a range of wavelengths so as to provide invariable results in printers using an array of laser diodes, or from printer to printer.

One method for providing a broad sensitivity in the infrared region of the spectrum is described in U.S. patent 5,013,642 to Muentert et al. The Muentert et al. patent describes the use of a combination of sensitizing dyes with maximum sensitivities differing by between about 5 to 100nm. It would be desirable though, to provide a radiation detecting element, particularly a silver halide photographic element useful in printers of the type described, which has a decreased change in sensitivity over a given wavelength range.

Summary of the Invention

The present invention provides a radiation detecting element which has a decreased change in sensitivity over a given wavelength range as a result of using an absorber dye of the specified absorption characteristics. In particular, the invention provides a radiation detecting element which has a radiation detecting composition to detect incident radiation such that the element has a wavelength of peak sensitivity, $\lambda_{peak sens}$, and decreasing sensitivity therearound. It will be noted that $\lambda_{peak sens}$ of the element is measured without the absorber dye, shortly described, being present. Also, the $\lambda_{peak abs}$ of the absorber dye will be a peak absorption of the dye in the same medium in which it will be present in the element. This may not necessarily be the same as a peak absorption of the dye in another medium (for example, the dye may have a peak absorption at a shorter wavelength when measured in alcohol than in a gelatin coating). Further, the element may have additional wavelengths of peak sensitivity (that is more than one peak sensitivity) as, for example, will be the case in an element designed to reproduce color.

EP 0 577 189 A2

The element is additionally provided with an absorber dye disposed in the detecting composition or alternatively, above the detecting composition (that is, disposed to be closer to a source of incident radiation to be detected). The absorber dye selected is one which has a wavelength of peak absorption, $\lambda_{peakabs}$, within 10nm (and preferably 5nm) of $\lambda_{peaksens}$ (although the difference could be 2nm or $\lambda_{peakabs}$ could equal $\lambda_{peaksens}$), and a profile of decreasing absorption around $\lambda_{peakabs}$. A dye with the foregoing parameters is chosen so as to decrease the change in sensitivity which the element would otherwise have in a region around $\lambda_{peakabs}$ if the absorber dye was not present (that is, to increase the wavelength range about $\lambda_{peaksens}$ over which sensitivity will remain relatively constant).

The radiation detecting element is preferably a photographic element which uses a silver halide emulsion sensitized with one or more, but preferably with only one, sensitizing dye.

Detailed Description of Embodiments of the Invention

A photographic element of the present invention comprises an emulsion sensitized with one or more absorber dyes as described. The absorber dye may be disposed in the emulsion itself, or above the emulsion (that is, positioned so that in normal use of the element, the absorber dye will be closer to the source of light to be detected). It will be understood, of course, that additional dyes such as an anti-halation dye, may be present on a back side of a base of the element, or on the same side of the base as the emulsion and beneath or above it. In addition, suitable filter dyes may also be used to prevent undesired radiation from reaching any emulsion in a photographic element of the present invention or to increase sharpness in the emulsion layer of the invention. Examples of anti-halation type dyes are described, for example, in U.S. patent number 4,839,265. Examples of filter dyes include those described in U.S. patent number 4,801,525. In any event though, the absorber dye is chosen to provide the effect described. When an anti-halation dye is chosen, for example, it will typically be one with a relatively broad constant absorption over much of the sensitivity versus wavelength curve of the sensitivity dye, and thus would not have the effect of the absorber dye of the present invention (therefore, the anti-halation dye is typically a different dye than the absorber dye).

Basically then, the absorber dye will, around $\lambda_{peakabs}$, tend to have an absorbance profile that is similar to the sensitivity profile of the sensitizing dye around $\lambda_{peaksens}$. Given that the $\lambda_{peakabs}$ and $\lambda_{peaksens}$ are close, and preferably the same, this means that the absorber dye will be absorbing light to an extent corresponding to the sensitivity of the emulsion (that is, more absorbance at higher sensitivity). Thus, speed losses due to the absorber dye are less at wavelengths other than $\lambda_{peaksens}$, at which wavelengths the speed the emulsion would otherwise have is also lower. The result is that the sensitivity of the element over a given wavelength does not change as much as it would if the absorber dye were not present.

Of course, the magnitude of the foregoing effect will generally depend on how closely matched $\lambda_{peakabs}$ and $\lambda_{peaksens}$ are, as well as how closely matched are the absorption profiles of the absorber and sensitizing dye (or dye combination), as well as the relative concentrations of absorber and sensitizing dyes. Furthermore, the power available from laser diodes is sufficient such that speed losses due to the presence of the absorber dye are acceptable.

It is preferred that the absorber dye chosen is one with an absorption profile around $\lambda_{peakabs}$ such that the change in sensitivity of the element around $\lambda_{peaksens}$ with the absorber dye present, is within 0.05logE over at least a 5nm range greater than if the absorber dye was absent. Preferably the absorber dye is chosen such that the foregoing range is at least 7nm. The element according to the invention, may also have a 1/2 peak sensitivity profile width which is less than 80nm, or less than 70nm (for example, 68 nm, 65nm, or even 50nm) and the ratio of the 1/2 peak sensitivity profile width of the element to the 1/2 peak absorption profile width of the absorber dye, of less than 1.5. By "1/2 peak sensitivity profile width", is meant the width of the sensitivity profile of the element, without the absorber dye present, around $\lambda_{peaksens}$ as measured at 1/2 the value of the sensitivity at $\lambda_{peaksens}$ (that is, at 0.3logE below the sensitivity at $\lambda_{peaksens}$). In the case of a typical photographic silver halide emulsion, the 1/2 peak sensitivity profile width will therefore be measured with the sensitizing dye in the emulsion. A peak sensitivity profile on a particular sensitized emulsion layer in the photographic element would normally closely correspond with a peak sensitivity profile of the overall element. By "1/2 peak absorption profile width of the absorber dye" is meant the width of the absorber dye profile in the element (for example, in a gelatin layer), without the emulsion present, around $\lambda_{peakabs}$ as measured at 1/2 the absorption at $\lambda_{peakabs}$. Photographic elements may be constructed using the invention, which have a $\lambda_{peaksens}$ in visible or infrared regions, although in one arrangement $\lambda_{peaksens}$ is limited to being longer than 700nm or 600nm.

EP 0 577 189 A2

In one arrangement, two or more sensitizing dyes are present which provide the element with $\lambda_{peaksens}$ but which dyes, on the emulsion and each in the absence of the other, exhibit peak sensitivities which are separated by less than 20nm or more than 30nm. In another arrangement the one or more sensitizing dyes provide the element with at least two peak sensitivities, $\lambda_{peaksens1}$ and $\lambda_{peaksens2}$ - (which may, for example, be separated by at least 20nm), and there are at least two absorber dyes present, each meeting the limitations as previously discussed so as to decrease the change in sensitivity around $\lambda_{peaksens1}$ and $\lambda_{peaksens2}$ which the element would otherwise have without the presence of those absorber dyes.

Examples of absorber dyes which might be used with suitably sensitized emulsions are those listed identified with "AD" numbers in Table A (the structures of the dyes are shown below).

Table A

DYE	Type of Dye	1/2 Peak Absorption Profile Width (nm)	$\lambda_{peakabs}$ (nm)
ADI	Absorber	60	779
ADII	Absorber	90	797
ADIV	Absorber	63	800
ADV	Absorber	60	776
ADVI	Absorber	67	784
ADVII	Absorber	70	766
ADVIII	Absorber	62	803
Filter Blue Green	Filter	200	716


Examples of sensitizing dyes which might be used in the practice of the invention are those listed with "SD" numbers in Table B (structures of which are shown below). The sensitivity data of Table B was obtained by giving the coatings used 2 second exposures on a wedge spectrographic instrument covering a wavelength range from 400 to 850 nm. The instrument contained a tungsten light source and a step tablet ranging in density from 0 to 3 density units in 0.3 density steps. After processing in a KODAK RAPID X-RAY DEVELOPER for 6 minutes at 20°C, speed was read at 10 nm wavelength intervals at a density of 0.3 above fog. Correction for the instrument's variation in spectral irradiance with wavelength was done by computer. The wavelength of peak sensitivity ($\lambda_{peaksens}$) was determined both from the resulting plot of log relative spectral sensitivity versus wavelength and from absorbance spectra of unexposed film coatings. The 1/2 peak sensitivity profile width was calculated by determining the two wavelengths above and below $\lambda_{peaksens}$ for which the spectral sensitivity decreased by half (that is, by 0.3 log E) compared to the sensitivity at $\lambda_{peaksens}$. The wavelength range of speed within 0.05 log E in Tables 1 and 2 was similarly determined except the two wavelengths were taken for which the spectral sensitivity decreased by 0.05 log E compared to the sensitivity at $\lambda_{peaksens}$. The sensitivity data of Table B was obtained with the dyes on a 0.2 μ m edge length cubic silver bromiodide emulsion (bromide to iodide molar ratio of 98 to 2).

EP 0 577 189 A2

Table B

Dye	Type of Dye	1/2 Peak Sensitivity Profile Width (nm)	$\lambda_{\text{peaksens}}$ (nm)
SDI	Sensitizing	65	780
SDII	Sensitizing	47	783
SDIV	Sensitizing	56	800
SDV	Sensitizing	53	810
SDVI	Sensitizing	51	776
SDVII	Sensitizing	62	771
CSI	Sensitizing	115	791

It will be noted that supersensitizers, such as SSI described below, can also be usefully provided in the emulsion. That sensitizer and other sensitizers which might be used are described in U.S. patent number 5,013,642. Another supersensitizer is that described in European Patent Application 87119271.2 and is of the structure:



It will be appreciated, of course, that the above listed absorber dyes do not necessarily match with any of the above listed sensitizing dye. In each case, to produce an element of the present invention, the absorber dye and sensitizing dye must be chosen such that the sensitized emulsion and absorber dye have the required parameters. Furthermore, Filter Blue Green is not expected to be a good choice as a suitable absorber dye in the present invention since its 1/2 peak absorption profile width of 200nm is very broad. Likewise, sensitizing dye CSI would not be expected to be used in the present invention since its 1/2 peak sensitivity profile width peak width is already very broad (115 nm) and further broadening would not likely be useful.

In addition, suitable sensitizing dyes could be synthesized according to techniques that are wellknown in the art, such as described in Hamer, Cyanine Dyes and Related Compounds, 1984 (John Wiley & Sons, New York) and James, The Theory of the Photographic Process 4th edition, 1977 (Eastman Kodak Company, Rochester, New York). Examples of sensitizing dyes that sensitize in the infrared region are described, for example, in U.S. patent number 4,839,265. The amount of a sensitizing dye that would typically be used in the invention is preferably in the range of 0.05 to 2.0 millimoles per mole of silver halide and more preferably from 0.01 to 0.5 millimoles per mole of silver halide. Optimum dye concentrations can be determined by methods known in the art.

The silver halide used in the photographic elements of the present invention may be silver bromoiodide, silver bromide, silver chloride, silver chlorobromide, and the like, which are provided in the form of an emulsion. The photographic elements of the present can use the sensitizing dye with tabular grain emulsions. Tabular grain emulsions are those in which greater than 50 percent of the total projected area of the emulsion grains are accounted for by tabular grains having a thickness of less than 0.3 μm (0.5 μm for

EP 0 577 189 A2

blue sensitive emulsion) and an average tabularity (T) of greater than 25 (preferably greater than 100), where the term "tabularity" is employed in its art recognized usage as

$$T = ECD/t^2$$

where

ECD is the average equivalent circular diameter of the tabular grains in μm and

t is the average thickness in μm of the tabular grains.

Of course, the grain size of the silver halide may have any distribution known to be useful in photographic compositions, and may be either polydispersed or monodispersed.

The silver halide grains to be used in the invention may be prepared according to methods known in the art, such as those described in Research Disclosure, (Kenneth Mason Publications Ltd, Emsworth, Hampshire, England) Item 308119, December, 1989 (hereinafter referred to as Research Disclosure I) and James, The Theory of the Photographic Process, above. These include methods such as ammoniacal emulsion making, neutral or acid emulsion making, and others known in the art. These methods generally involve mixing a water soluble silver salt with a water soluble halide salt in the presence of a protective colloid, and controlling the temperature, pAg, pH values, etc, at suitable values during formation of the silver halide by precipitation. The silver halide may be advantageously subjected to chemical sensitization with compounds such as active gelatin, sulfur, selenium, tellurium, gold, platinum, palladium, iridium, osmium, rhenium, phosphorous, or combinations thereof and others known in the art. Compounds and techniques useful for chemical sensitization of silver halide are described, for example, in Research Disclosure I and the references cited therein.

The photographic elements of the present invention, as is typical, use the silver halide in the form of an emulsion. Photographic emulsions generally include a vehicle for coating the emulsion as a layer of a photographic element. Useful vehicles include both naturally occurring substances such as proteins, protein derivatives, cellulose derivatives (e.g., cellulose esters), gelatin (e.g., alkali-treated gelatin such as cattle bone or hide gelatin, or acid treated gelatin such as pigskin gelatin), gelatin derivatives (e.g., acetylated gelatin, phthalated gelatin, and the like), and others as described in Research Disclosure I. Also useful as vehicles or vehicle extenders are hydrophilic water-permeable colloids. These include synthetic polymeric peptizers, carriers, and/or binders such as poly(vinyl alcohol), poly(vinyl lactams), acrylamide polymers, polyvinyl acetals, polymers of alkyl and sulfoalkyl acrylates and methacrylates, hydrolyzed polyvinyl acetates, polyamides, polyvinyl pyridine, methacrylamide copolymers; and the like, as described in Research Disclosure I. The vehicle can be present in the emulsion in any amount useful in photographic emulsions. The emulsion can also include any of the addenda known to be useful in photographic emulsions.

The silver halide may be sensitized by dyes by methods known in the art, such as described in Research Disclosure I. The dye may be added to an emulsion of the silver halide grains and a hydrophilic colloid at any time prior to (e.g., during or after chemical sensitization) or simultaneous with the coating of the emulsion in a photographic element. The dye/silver halide emulsion may be mixed with a dispersion of color image-forming coupler immediately before coating or in advance of coating (for example, 2 hours). Essentially any type of emulsion may be used. For example, negative-working emulsions such as surface-sensitive emulsions or unfogged internal latent image-forming emulsions, direct-positive emulsions such as surface fogged emulsions, or others described in, for example, Research Disclosure I, may be used.

Other addenda in the emulsion may include antifoggants, stabilizers, light absorbing or reflecting pigments, vehicle hardeners such as gelatin hardeners, coating aids, dye-forming couplers, and development modifiers such as development inhibitor releasing couplers, timed development inhibitor releasing couplers, and bleach accelerators. These addenda and methods of their inclusion in emulsion and other photographic layers are well-known in the art and are disclosed in Research Disclosure I and the references cited therein. The emulsion may also include brighteners, such as stilbene brighteners. Such brighteners are well-known in the art and are used to counteract dye stain.

The emulsion layer containing silver halide sensitized with a dye of the present invention can be coated simultaneously or sequentially with other emulsion layers, subbing layers, filter dye layers, interlayers, or overcoat layers, all of which may contain various addenda known to be included in photographic elements. These include, depending on the particular application, antifoggants, oxidized developer scavengers, DIR couplers, antistatic agents, optical brighteners, light-absorbing or lightscattering pigments, and the like. The layers of the photographic element can be coated onto a support using techniques well-known in the art. These techniques include immersion or dip coating, roller coating, reverse roll coating, air knife coating, doctor blade coating, stretch-flow coating, and curtain coating, to name a few. The coated layers of the

EP 0 577 189 A2

element may be chill-set or dried, or both. Drying may be accelerated by known techniques such as conduction, convection, radiation heating, or a combination thereof.

As already mentioned, photographic elements of the present invention can be black and white or color. A color photographic element generally contains three records (each record often consisting of emulsion layers of the same spectral sensitivity but different speed): a first record having a yellow dye-forming color coupler associated therewith; a second record having a magenta dye-forming color coupler associated therewith; and a third record having a cyan dye-forming color coupler associated therewith. For printer film, each of those records would be sensitized to different wavelengths which do not necessarily correspond to the light color absorbed by the dye produced by the color coupler. For example, each record could be sensitized to a different region of the infrared spectrum. The dye forming couplers are provided in the emulsions of the records typically by first dissolving or dispersing them in a water immiscible solvent, the resulting mixture then being dispersed in the emulsion. Dyeforming couplers are well-known in the art and are disclosed, for example, in Research Disclosure 1.

Photographic elements comprising the composition of the invention can be processed in any of a number of known photographic processes utilizing any of a number of known processing compositions, described, for example, in Research Disclosure 1, or in James, The Theory of the Photographic Process 4th Ed., 1977.

The invention is further described in the following Examples.

Example 1

This example mimics a layer which might be used on an infrared sensitive graphic arts scanner film. In practice, such a film would comprise a heavy laydown of a doped (for example, with Rh) silver halide emulsion to give a high contrast (approximately 10), high maximum density image ($D_{max} > 5$). Since it is hard to accurately determine speeds of such layers, a model layer was constructed comprising 150 mg/ft² of an (S + Au) sensitized 0.3 μ m edge length cubic AgCl₇₀Br₃₀ emulsion thoroughly mixed with 250 mg/ft² of the same emulsion which had not been chemically sensitized. Neither emulsion was doped and provided an overall contrast (that is, γ) of 2.5 at a density of 1.0 above fog. This emulsion was treated with 500 mg/Ag mole of the super sensitizer SSI and the two antifoggants AFI and 5-carboxy-2-methylmercapto-tetraazaindine. The emulsions were coated on a base of poly(ethyleneterephthalate) in 400 mg/ft² gel and overcoated with 80 mg/ft² gel. These gel layers were hardened with 1.5 weight percent bis(vinylsulfonyl)methyl ether (referred to as "BVSE").

The emulsion was spectrally sensitized with 0.025 millimoles/Ag mole of the sensitizing dye SDI.

Sensitivities were measured similarly to those obtained for Table B examples, except the film coatings were exposed for 0.5 seconds on a spectral sensitometer and developed for 35 seconds at 95 °F in Kodak Rapid Scanner Developer diluted 1:4. Normalized photographic speeds at a density of 1.0 above Fog were calculated and plotted at 10 nm intervals. The λ_{max} of the sensitized emulsion (that is, the sensitized dye on an unexposed unprocessed emulsion coating) and the two absorber dyes (each coated separately in gelatin) were measured spectrophotometrically, and recorded as the $\lambda_{peak sens}$ or $\lambda_{peak abs}$.

The above procedure was repeated using combinations of sensitizing and absorber dyes as shown in Table I below. The effects of 1 mg/ft² of intergrain absorber dyes on the breadth of the spectral sensitization, defined as the wavelength range over which speed stayed constant within $\pm 0.05 \log E$, is shown in Table 1.

EP 0 577 189 A2

TABLE 1

Sensitizing Dye	$\lambda_{peak\ sens}$	1/2 Peak Sensitivity Profile Width	Absorber Dye	$\lambda_{peak\ abs}$	1/2 Peak Absorption Profile Width	Wavelength of Maximum Speed of Element	Speed at Wavelength of Maximum Speed	Wavelength range of speed within $\pm 0.05 \log E$	Width of range
SDI	780 nm	49 nm	None	780 nm	251	766-794 nm	28 nm
"	780 nm	...	ADI	779 nm	60 nm	780 nm	205	755-802 nm	47 nm
"	780 nm	...	ADII	797 nm	90 nm	770 nm	172	756-792 nm	36 nm

Note that absorber dye ADI has a $\lambda_{peak\ abs}$ at almost the same wavelength $\lambda_{peak\ sens}$ as sensitizing dye SDI (only 1 nm difference). However, the comparative absorber dye ADII has a $\lambda_{peak\ abs}$ which is 17 nm longer. Furthermore, ADII has a much broader absorbance profile than ADI. Thus, the presence of ADII causes an undesirable shift of peak sensitivity of the element from the desired 780 nm to an undesired 770nm. In addition, ADII provides a sensitivity broadening which is not large, is unsymmetric and

EP 0 577 189 A2

furthermore causes considerably decreased sensitivity. On the other hand, the absorber dye ADI in combination with the emulsion using SDI, an example of the invention, provides a large and symmetric broadening of the wavelength range within $\pm 0.05\log E$ since its peak is at the same wavelength as the sensitizing dye, and since it has a relatively narrow absorption profile. Speed losses in the presence of absorber dyes were large in this example due to the absence of an antihalation or pelloid layer (that is, the layer on the back side of the base) which would have minimized speed gains from back reflected light. Such an example is given below.

Example 2

This example used a pelloid layer comprising 3 mg/ft² of antihalation dye AHI in 400 mg/ft² gel hardened with 1.5 weight percent BVSME. The emulsion layer was similar to that in Example 1 except that a single (S + Au) sensitized finer grain 0.18 μm AgCl₇₀Br₃₀ emulsion was used, at a laydown of 320 mg/ft². The emulsion was spectrally sensitized with 0.025 mmole per mole Ag₂S of the 783 nm sensitizing dye SDII (as measured on the emulsion). The broadening effect of adding 1 mg/ft² of the 780 nm intergrain absorber dye ADS was measured. Results are summarized in Table 2 below.

EP 0 577 189 A2

TABLE 2

Sensitizing Dye	λ_{peak} of sensitized emulsion	1/2 Peak Sensitivity Profile Width	Absorber Dye	λ_{peak} of absorber dye	1/2 Peak Absorption Profile Width	Wavelength of Maximum Speed of Element	Speed at Wavelength of maximum Speed	Wavelength range of speed within $\pm 0.05 \log E$	Width of range
SD11	783 nm	45 nm	Noile	780 nm	60 nm	780 nm	174	767-793 nm	26 nm
"	"	"	ADI	780 nm	60 nm	780 nm	153	762-796 nm	34 nm


Example 2 then, provides a lower laydown of a significantly less light scattering emulsion and an additional anti reflection layer on the back side of the base. However, even in such a case a significant and useful broadening of the wavelength range around λ_{peak} in which the sensitivity is relatively constant, is achieved on both the short and long wavelength sides, by the present invention. Note also that the finer grain emulsion and the anti-halation layer on the back side of the base gave much smaller speed losses in

EP 0 577 189 A2

the presence of the same level of ADI used in Example 1.


Example 1 demonstrates that the broadening of the wavelength range of relatively constant sensitivity (that is, within 0.05logE) was reduced and restricted to either the longer or shorter wavelength about $\lambda_{peak_{sens}}$, when $\lambda_{peak_{sens}}$ and $\lambda_{peak_{abs}}$ differed by only 17 nm. Furthermore an undesirable shift in of peak sensitivity of the element with the absorbed dye present, occurred.

Formulae of compounds described above are:




EP 0 577 189 A2


Supersensitizer SSI



Antifoggant AFI




Absorber Dye	R	R ₁
ADI	2SEt	Me
ADVI	4SB	Me
ADVII	4SB	H
4SB = 4-sulfobutyl; 2SEt = 2-sulfoethyl		




EP 0 577 189 A2


Absorber Dye ADII



Absorber Dye	R	R ₁
ADIV	SEt	C1
ADV	SEt	Ph
ADVIII	4SB	C1




Filter Blue Green




Sensitizing Dye	R ₁	R ₂	z ₁	z ₂
SDI	Et	Et	6-Me	5-Me and 6-Me
SDVII	SP	Et	H	H


EP 0 577 189 A2




Sensitizing Dye SDII



Sensitizing Dye SDIV




Sensitizing Dye SDV




Sensitizing Dye SDVI

EP 0 577 189 A2



Sensitizing Dye CSI



Anti-halation dye AHI

The invention has been described in detail with particular reference to preferred embodiments, but it will be understood that variations and modifications can be effected within the spirit and scope of the invention.

Claims

1. A radiation detecting element comprising:

a radiation detecting composition to detect incident radiation; and
an absorber dye disposed in the detecting composition or thereabove to be closer to a source of radiation to be detected;

wherein the element has a wavelength of peak sensitivity measured without the absorber dye present, $\lambda_{\text{peaksens}}$, and decreasing sensitivity therearound, and the absorber dye has a wavelength of peak absorption, λ_{peakabs} , within 10nm of $\lambda_{\text{peaksens}}$ and a profile of decreasing absorption around λ_{peakabs} so as to decrease the change in sensitivity which the element otherwise has around $\lambda_{\text{peaksens}}$ without the absorber dye present.

2. A photographic element comprising:

a silver halide emulsion sensitized with one or more sensitizing dyes; and
an absorber dye disposed in the emulsion or thereabove to be closer to a source of radiation to be detected by the element;

wherein the element has a wavelength of peak sensitivity measured without the absorber dye present, $\lambda_{\text{peaksens}}$, and decreasing sensitivity therearound, and the absorber dye has a wavelength of peak absorption, λ_{peakabs} , within 10 nm of $\lambda_{\text{peaksens}}$ and a profile of decreasing absorption around λ_{peakabs} so as to decrease the change in sensitivity which the element otherwise has around $\lambda_{\text{peaksens}}$ without the absorber dye present.

EP 0 577 189 A2

3. A photographic element according to claim 2 wherein the silver halide emulsion is sensitized with only a single sensitizing dye.
4. A photographic element according to claim 2 or 3 wherein the absorber dye has a $\lambda_{peakabs}$ within 5nm of $\lambda_{peaksens}$.
5. A photographic emulsion according to claim 2 wherein two or more sensitizing dyes are present which provide the element with $\lambda_{peaksens}$ but which dyes, on the emulsion and each in the absence of the other, exhibit peak sensitivities which are separated by less than 20nm or more than 30nm.
6. A photographic element according to claim 2 wherein the one or more sensitizing dyes provide the element with at least two peak sensitivities, $\lambda_{peaksens1}$ and $\lambda_{peaksens2}$, and wherein the element has at least two absorber dyes which have respective peak absorptions, $\lambda_{absmax1}$ and $\lambda_{absmax2}$, within 10nm of $\lambda_{peaksens1}$ and $\lambda_{peaksens2}$, respectively, so as to decrease the change in sensitivity which the element otherwise has around $\lambda_{peaksens1}$ and $\lambda_{peaksens2}$ without the presence of the absorber dyes.
7. A photographic element according to any one of claims 2 to 4 wherein the 1/2 peak sensitivity profile width of the element is less than 70nm and the ratio of the absorber dye 1/2 peak absorption profile width to the element's 1/2 peak sensitivity profile width is less than 1.5.
8. A photographic element according to any one of claims 2 to 4 or 7 wherein the absorber dye has a profile of absorption around $\lambda_{peakabs}$ such that the change in sensitivity of the element around $\lambda_{peaksens}$ with the absorber dye present is within 0.05logE over at least an additional 5nm range than if the absorber dye was not present.
9. A photographic element according to any one of the preceding claims additionally comprising an anti-halation dye in the emulsion or thereabove, the anti-halation dye being a different dye than the absorber dye.